## PHYSICAL TESTING REPORT



insight creating advantage



Mactac Europe Boulevard Kennedy Zoning Industrial, Zone B 7060 Soignies Beligium

FAO: Mrs. Beatrice Detournay

Report of Tests on: Self Adhesive Textured Laminate

Your Reference: FI

Floor Grip

Lucideon Reference: (144809)-24837

Date Reported:
Date Logged:

03-Nov-2014 08-Oct-2014 **Order Number:** 

Date(s) of Test(s):

4270

0.1.0044

30-Oct-2014 to 30-Oct-2014

Inclined Platform Test for Slip Resistance In Shod Conditions

DIN 51130:2010

	Operator 1 - Angle of Inclination	Operator 2 - Angle of Inclination
No.	0	۰
1	21.2	19.8
2	20.8	20.7
3	20.2	20.7

Description of Test Specimen(s): 1m x 0.5m laminate sheet

Average of Six Shod Results (Corrected): 20.6 °

Category: R11

The critical angle at which a test person reaches the limit of safe walking on an inclined plane is used as a measure of slip resistance.

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

**End of Test Report** 



T +44 (0)1782 764428

www.fucideon.com

enquiries@lucideon.com